

FutureGuide™-Ace

Compliant with ITU-T G.657.A1 / G.652.D

FutureGuide™-Ace can be one of the best solutions, for its significantly improved bending loss performance, the same MFD as standard single mode fibers and reduced attenuation compared with conventional fibers.

Improved bending performance enables fiber storage with smaller diameter and space saving of fiber splicing points. Matched MFD brings full compatibility with conventional fibers and lower splice loss. Reduced attenuation characteristics gives more margin to optical loss budget of optical fiber networks.

FutureGuide™-Ace would contribute greatly to high-speed and high-capacity transmission in various networks from long-haul to access networks of 40G / 100Gbps and beyond.

Features

- Improved macro-bending loss exceeding ITU-T G.657.A1 and excellent micro-bending performance.
- Full compatibility with single mode fibers installed in existing optical fiber networks.
- Reduced attenuation characteristics compared with conventional fibers such as ITU-T G. 652 fibers.

Customer's advantages

- Provides consistent and stable performance in the field.
- Achieves lower splice loss with existing G.652 fibers maintaining excellent bending loss performance.
- Gives more margin for optical loss budget of optical fiber networks and is suitable for advanced modulation formats or extension of

Optical Characteristics

Attenuation	
Attenuation coefficient at 1310 nm	≤ 0.32 dB/km
Attenuation coefficient at 1383 nm	≤ 0.32 dB/km *1
Attenuation coefficient at 1550 nm	≤ 0.18 dB/km
Attenuation coefficient at 1625 nm	≤ 0.20 dB/km
Attenuation vs. wavelength *2	
1285 – 1330 nm ref. λ of 1310 nm	$\alpha \leq 0.03$ dB/km
1525 – 1575 nm ref. λ of 1550 nm	$\alpha \leq 0.02$ dB/km
Macro-bending loss	
∅=50 mm, 100 turns at 1310, 1550, 1625 nm	≤ 0.01 dB
∅ =30 mm, 10 turns at 1550 nm	≤ 0.05 dB
∅ =30 mm, 10 turns at 1625 nm	≤ 0.30 dB
∅ =20 mm, 1 turn at 1550 nm	≤ 0.50 dB
∅ =20 mm, 1 turn at 1625 nm	≤ 1.5 dB

Point discontinuity at 1310 nm	≤ 0.05 dB
Point discontinuity at 1550 nm	≤ 0.05 dB
Cut off wavelength	
Cable cut-off wavelength	≤ 1260 nm
Chromatic dispersion	
Chromatic dispersion coefficient at 1285-1330 nm	≤ 3.5 ps/(nm·km)
Chromatic dispersion coefficient at 1550 nm	13.3 - 18 ps/(nm·km)
Chromatic dispersion coefficient at 1625 nm	17.2 - 22 ps/(nm·km)
Zero-dispersion wavelength	1302 - 1324 nm
Zero-dispersion slope	0.073 - 0.092 ps/(nm ² ·km)
Polarization mode dispersion (PMD) *3	
Uncabled fiber PMD coefficient	≤ 0.1 ps/√km
Link design value PMD ₀	≤ 0.04 ps/√km

*1. The attenuation at 1383nm after hydrogen aging in accordance with IEC60793-2-50

*2. The attenuation within the specified wavelength range is limited to a difference of α or less compared to the reference wavelength (ref. λ).

*3. This characteristic is guaranteed only in a virtually tension-free condition.



Contact us

Structural Characteristics

Mode field diameter at 1310 nm	9.2 ± 0.4 μm
Mode field diameter at 1550 nm	10.4 ± 0.5 μm
Cladding diameter	125.0 ± 0.7 μm
Coating diameter (uncolored)	240 ± 5 μm
Coating diameter (colored)	250 ± 10 μm
Core concentricity error	≤ 0.5 μm
Cladding non-circularity	≤ 0.7 %
Coating-Cladding concentricity	≤ 12 μm
Fiber curl radius	≥ 4.0 m

Mechanical Characteristics

Proof test *4	≥ 1 % (100 kpsi or 0.7 GPa)
Dynamic stress corrosion susceptibility parameter (n _d)	≥ 20
Coating strippability F	1.3 N ≤ F ≤ 8.9 N
Length (uncolored)	Up to 50.4 km
Length (colored)	Up to 63 km

*4. The product is subjected to tensile testing throughout its entire length.

Environmental Characteristics

	Attenuation Change at 1310, 1550, 1625 nm
Temperature dependence - 60 to 85 °C	≤ 0.05 dB/km Ref. temp. 23 °C
Temperature Humidity Cycling -10 °C to +85 °C up to 98 % R.H.	≤ 0.05 dB/km Ref. temp. 23 °C
Water immersion at 23 °C ± 2 °C	≤ 0.05 dB/km
Dry heat at 85 °C ± 2 °C	≤ 0.05 dB/km Ref. temp. 23 °C
Damp Heat 85 °C at 85 %R.H.	≤ 0.05 dB/km Ref. temp. 23 °C

Performance Characteristics

	Typical value
Attenuation coefficient at 1490 nm	0.20 dB/km
Zero dispersion wavelength	1313 nm
Zero dispersion slope	0.087 ps/(nm ² ·km)
Effective group index of refraction N _{eff} at 1310 nm	1.4675
Effective group index of refraction N _{eff} at 1550 nm	1.4681
Effective group index of refraction N _{eff} at 1625 nm	1.4685

Note: This document is published for your reference purpose only and the specifications for commercial purpose will be issued upon agreement with customers.

Note: If you require more detailed information, please contact us by scanning the QR code below.



Contact us